Distoration Rate For Pre Print Plates For .107 Is 96.70%

Distoration Rate For Tail Print Plates For .067 Is 97.99%

1 Duro Way Walton, KY 41094 Duro.ArtDepartment@novolex.com

CREATED BY: B. Wallrawe

TECHNICAL:

DESIGN GROUP: Shopper Series

Knotless Macrame Slit Top Kary 9 x 5 3/4 x 13 3/4

SCALE: FULL

DATE: 2/10/16

PLEASE NOTE: This proof is for copy, content, and position approval only. This proof is not for actual color or paper substrate used to produce your order.

Carefully check all traps (overlap of color) punctuation, spelling, copy and elements. Please use attached approval letter for signed approval. Approval letter, proof and ink roll outs must be returned to produce your order. ink roll outs must be returned to produce your order.

BORDER DESIGNS Because Of Machine Movement In Bag Conversion, Copy Should Be Placed At Least 1/4" From Fold Lines Or Edges. In The Top Area, Use 1/2" Bleed.
Border Designs Should Be Kept 1/2" From
Fold Edges, Top Cutoff And Bottom Fold.

40% Screen In All Colors

Containing Screens

Full Panel Print Must Bleed Into Top & Bottom Of Bag. Which Is Indicaated On Template



