Distoration Rate For Pre Print Plates For .107 Is 97.24%

Distoration Rate For Tail Print

Plates For .067 Is 98.32%

1 Duro Way Walton, KY 41094 Duro.ArtDepartment@novolex.com CREATED BY: B. Wallrawe

Shopper Series Knotless Macrame Slit Top Mart 13 x 7 x 17

Printed Flap 10 1/16"

DESIGN GROUP:

PLEASE NOTE: This proof is for copy, content, and position approval only. This proof is not for actual color or paper substrate used to produce your order.
Carefully check all traps (overlap of color) punctuation, spelling, copy and elements. Please use attached approval letter for signed approval. Approval letter, proof and ink roll outs must be returned to produce your order. BORDER DESIGNS

Because Of Machine Movement In Bag
Conversion, Copy Should Be Placed At
Least 1/4" From Fold Lines Or Edges.
In The Top Area, Use 1/2" Bleed.

Border Designs Should Be Kept 1/2" From
Fold Edges, Top Cutoff And Bottom Fold.

Full Panel Print Must Bleed Into Top &
Bottom Of Bag. Which Is Indicaated On Template

Fill All 5 Anti-Bounce Area With 40% Screen In All Colors Containing Screens

