Distoration Rate For Pre Print Plates For .107 Is 97.24%

Distoration Rate For Tail Print

Plates For .067 Is 98.32%

DURO

A NOVOLEX BRAND

1 Duro Way Walton, KY 41094 Duro.ArtDepartment@novolex.com CREATED BY: B. Wallrawe

Shopper Series J V Slit Regal 12 x 9 x 15 3/4

Printed Flap 9 7/8"

DESIGN GROUP:

PLEASE NOTE: This proof is for copy, content, and position approval only. This proof is not for actual color or paper substrate used to produce your order.

Carefully check all traps (overlap of color) punctuation, spelling, copy and elements. Please use attached approval letter for signed approval. Approval letter, proof and ink roll outs must be returned to produce your order. DATE: 4/2/13 SCALE: FULL

BORDER DESIGNS Because Of Machine Movement In Bag Fill All 5 Anti-Bounce Area With 40% Screen In All Colors Conversion, Copy Should Be Placed At Least 1/4" From Fold Lines Or Edges.
In The Top Area, Use 1/2" Bleed.
Border Designs Should Be Kept 1/2" From
Fold Edges, Top Cutoff And Bottom Fold. Containing Screens

Full Panel Print Must Bleed Into Top &

Bottom Of Bag. Which Is Indicaated On Template

Starting Web: 43 1/4" Finished Web 43.00" Gusset 9.00" Face 12.00" Gusset 9.00" Back 12.00" Extend To this Line. Line Will Not Be Seen. Plates Should Stop At This AFTER CONVERSION, THIS AREA (.25") WILL APPEAR IN BOTTOM OF BAG Artwork Bleeds
To This Line
To Complete
Step & Repeat
Of Copy Bleed
Into Left Gusset Panel. BAR #1 BAR #2 BAR #3 UNPRINTED PASTE AREA | BAR #4 | BAR #5 | BAR #6 | UNPRINTED PASTE AREA UNPRINTED PASTE AREA PLACEMENT OF DENSITY BARS (UP TO 6 COLORS) Cut Flap 8 1/8"